

THERMOPLASTIC ELASTOMERS

Delivering value with innovative TPE
solutions for thousands of applications



GENERAL PROPERTIES					TENSILE PROPERTIES								REGULATORY					BONDING	PROCESS				
Color	Hardness	Specific Gravity	Compression Set @ 23°C	Compression Set @ 100°C	100% Modulus		300% Modulus		Tensile	Strength	Elongation	Tear Strength		Food Contact	ISO 10993	USP VI	RoHS	UL 94	Suitable Substrates	Injection	Extrusion	Blow	
	ASTM Shore A	ASTM	ASTM %	ASTM %	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM %	ASTM pli	ASTM kN/m										
Versaflex™ Healthcare Series																							
CL 2242	Clear	43A	0.89	23	-	152	1.05	294	2.02	731	5	780	124	22	✓	✓	✓	✓	-	PP	✓	✓	-
CL 2250	Clear	50A	0.89	20	-	220	1.52	337	2.32	827	5.7	770	140	25	✓	✓	✓	✓	-	PP	✓	✓	-
CL E85	Clear	84A	0.90	20	72	752	5.18	1160	8	1550	10.7	450	433	76	✓	✓	✓	✓	-	PP	✓	✓	✓
CL E90	Clear	90A	0.90	27	73	1000	6.89	1230	8.5	1830	12.6	57	-	-	✓	✓	✓	✓	-	PP	✓	✓	✓
CL E95	Clear	95A	0.90	38	71	1680	11.6	1730	11.9	2500	17.2	580	720	126	✓	✓	✓	✓	-	PP	✓	✓	✓
G2705 N	Natural	60A	0.88	-	-	-	-	528	3.64	670	4.62	470	-	-	✓	✓	✓	✓	-	PP	✓	✓	-
HC 2110-35N	Natural	34A	0.90	19	47	145	1	261	1.8	400	2.76	620	97	17	-	✓	✓	✓	-	LDPE, PP	✓	-	-
HC 2110-57B	Black	59A	1.01	20	37	369	2.54	558	3.85	537	3.7	350	147	26	-	✓	✓	✓	-	PP	✓	✓	-
HC 3810-20	Natural	20A	0.88	16	54	123	0.8	185	1.3	342	2.4	650	-	-	✓	-	-	-	-	-	-	-	-
HC 3810-30	Natural	30A	0.89	18	58	170	1.2	245	1.7	459	3.2	680	-	-	✓	-	-	-	-	-	-	-	-
HC 3810-40	Natural	40A	0.88	19	59	191	1.3	275	1.9	506	3.5	670	-	-	✓	-	-	-	-	-	-	-	-
HC 3810-50	Natural	50A	0.89	21	61	264	1.8	366	2.5	699	4.8	690	-	-	✓	-	-	-	-	-	-	-	-
HC 3810-60	Natural	60A	0.88	24	65	459	3.2	594	4.1	790	5.4	510	-	-	✓	-	-	-	-	-	-	-	-
HC 3810-70	Natural	70A	0.88	28	67	535	3.7	684	4.7	1000	6.9	570	-	-	✓	-	-	-	-	-	-	-	-
HC 3810-80	Natural	80A	0.88	30	67	689	4.8	869	6.0	1390	9.6	620	-	-	✓	-	-	-	-	-	-	-	-
HC 3810-90	Natural	90A	0.88	27	89	1087	7.5	1350	9.3	1890	13	570	-	-	✓	-	-	-	-	-	-	-	-
HC BT218	Natural	67A	0.89	19	69	381	2.6	683	4.7	1186	8.2	608	-	-	-	✓	✓	-	-	-	-	✓	-
HC MT222	Clear	66A	0.88	14	-	334	2.3	629	4.34	898	6.19	430	220	36	✓	✓	✓	✓	-	PP	✓	✓	-
HC MT224	Clear	75A	0.89	19	-	468	3.23	773	5.33	1360	9.4	530	321	56	✓	✓	✓	✓	-	PP	✓	✓	-
HC MT226	Clear	84A	0.88	20	-	606	4.17	885	6.1	1600	11	600	433	76	✓	✓	✓	✓	-	PP	✓	✓	-
HC MT317	Clear	68A	0.89	17	69	450	3.1	660	4.55	870	6	470	221	39	-	✓	✓	✓	-	PP	✓	✓	-
OM 1040X-1	Natural	42A	0.92	22	-	180	1.24	301	2.08	504	3.47	580	100	18	✓	✓	✓	✓	-	ABS, PC	✓	-	-
OM 3060-1	Clear	59A	0.90	33	-	420	2.9	360	2.48	500	3.45	480	180	32	✓	✓	✓	✓	HB	ABS, PC	✓	-	-
OM 8940X-1	Clear	42A	0.91	-	-	233	-	311	-	1573	-	1059	168	-	-	-	-	-	-	PK, COPE	✓	-	-
OM 4052	Natural	56A	1.01	27	-	271	-	557	-	1680	-	670	-	-	-	✓	-	✓	-	PC, ABS, PC/ABS & PK	✓	✓	-
OM 4063	Natural	54A	1.12	30	-	365	-	580	-	1640	-	670	-	-	-	✓	-	✓	-	PC, ABS, PC/ABS & PK	✓	✓	-



GENERAL PROPERTIES					TENSILE PROPERTIES								REGULATORY					BONDING		PROCESS		
Color	Hardness	Specific Gravity	Compression Set @ 23°C	Compression Set @ 100°C	100% Modulus		300% Modulus		Tensile	Strength	Elongation	Tear Strength		Food Contact	ISO 10993	USP VI	RoHS	UL 94	Suitable Substrates	Injection	Extrusion	Blow
	ASTM Shore A	ASTM	ASTM %	ASTM %	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM %	ASTM pli	ASTM kN/m									
Versaflex™ Unfilled Series																						
CL 2000X	Clear	3A	0.87	23	-	15	0.1	35	0.24	300	2.07	1100	50	9	✓	-	-	✓	-	-	✓	-
CL 2003X	Clear	33 00	0.87	-	-	9	0.06	15	0.1	130	0.89	850	40	7	✓	-	-	✓	-	-	✓	-
CL 30	Clear	30A	0.89	11	-	100	0.69	200	1.38	751	5.18	870	110	19	✓	-	-	✓	-	PP	✓	-
CL 40	Clear	43A	0.89	12	-	200	1.38	329	2.27	815	5.62	760	130	23	✓	-	-	✓	HB	PP	✓	-
GP 2810-20N	Translucent	20A	0.88	-	-	-	-	127	0.88	315	2.17	670	-	-	✓	-	-	✓	-	PP	✓	-
GP 2810-30N	Translucent	30A	0.88	-	-	-	-	198	1.37	553	3.81	820	-	16	✓	-	-	✓	-	PP	✓	-
GP 2810-40N	Translucent	40A	0.88	15	-	-	-	248	1.71	610	4.21	710	-	18	✓	-	-	✓	-	PP	✓	-
GP 2810-50N	Translucent	50A	0.88	16	-	-	-	330	2.28	650	4.48	670	-	-	✓	-	-	✓	-	PP	✓	✓
GP 2810-60N	Translucent	60A	0.89	-	-	-	-	330	2.28	649	4.48	670	-	-	✓	-	-	✓	-	PP	✓	✓
GP 2810-70N	Translucent	68A	0.89	-	-	363	2.5	508	3.5	870	6	500	-	30	✓	-	-	✓	-	PP	✓	-
GP 2810-80N	Translucent	80A	0.88	36	76	612	4.2	-	-	1290	8.9	660	206	36	✓	-	-	✓	✓	PP, PE	✓	-
GP 2810-90N	Translucent	90A	0.89	37	90	904	6.2	-	-	1570	10.8	590	297	52	✓	-	-	✓	✓	PP, PE	✓	-
Versaflex™ PC/ABS OM Series																						
OM 1060X-1	Natural	60A	0.93	29	-	310	2.14	470	3.24	595	4.1	490	150	26	✓	-	-	✓	HB	ABS, PC, COPE	✓	-
OM 1245X-1	Translucent	46A	0.97	31	-	260	1.79	507	3.5	886	6.11	490	-	-	✓	-	-	✓	-	ABS, PC	✓	-
OM 9-801N	Natural	47A	1.04	43	-	210	1.45	261	1.8	651	4.49	820	100	18	✓	-	-	✓	HB	Universal	✓	-
OM 9-802CL	Clear	40A	0.93	20	-	230	1.59	310	2.14	930	6.41	1100	140	25	✓	-	-	✓	-	Universal	✓	-
Versaflex™ Nylon OM Series																						
OM 6059-9	Black	58A	1.10	14	-	254	1.75	-	-	355	2.45	290	-	-	-	-	-	✓	HB	Nylon	✓	-
OM 6240-1	Natural	43A	1.09	22	-	150	1.03	243	1.68	285	1.97	510	90	16	-	-	-	✓	-	Nylon	✓	-
OM 6258-1	Natural/Black	62A	1.09	23	-	275	1.9	385	2.65	400	2.8	350	105	18	-	-	-	✓	HB	Nylon	✓	-
OM 6275-9	Black	77A	1.09	25	-	480	3.31	630	4.34	580	4	260	165	29	-	-	-	✓	-	Nylon	✓	-
Versaflex™ VDT Series																						
VDT 4201-35B	Black	35A	1.00	12	-	147	-	308	-	699	-	779	133	-	-	-	-	✓	-	PE	-	-
VDT 4202-40B	Black	40A	1.00	11	-	-	-	396	-	701	-	560	97	-	-	-	-	✓	-	PP	-	-
VDT 5110-50N	Natural	52A	1.05	21	-	250	-	402	-	825	-	735	161	-	-	-	-	✓	-	PC, ABS	-	-
VDT 5120-40	Natural/Black	42A	1.09	20	-	179	-	362	-	591	-	750	131	-	-	-	-	✓	-	Nylon	-	-



GENERAL PROPERTIES					TENSILE PROPERTIES									REGULATORY					BONDING		PROCESS		
Color	Hardness	Specific Gravity	Compression Set @ 23°C	Compression Set @ 100°C	100% Modulus		300% Modulus		Tensile	Strength	Elongation	Tear Strength		Food Contact	ISO 10993	USP VI	RoHS	UL 94	Suitable Substrates	Injection	Extrusion	Blow	
	ASTM Shore A	ASTM	ASTM %	ASTM %	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM %	ASTM pli	ASTM kN/m										
Versaflex™ Consumer Electronics Series																							
CE 3120-40	Translucent	42A	0.92	22	-	-	300	2.07	504	3.47	580	-	-	-	-	-	✓	-	ABS, PC, COPE	✓	✓	-	
CE 3120-65	Translucent	67A	1.16	-	-	-	630	4.34	1650	11.4	700	-	-	-	-	-	✓	-	ABS, PC, COPE	✓	✓	-	
CE 3130-70	Natural	70A	1.04	-	-	-	-	-	2220	15.3	660	-	-	-	-	-	✓	-	PC, ABS, PC/ABS, COPE	✓	-	-	
CE 3130-80	Natural	80A	1.08	-	-	-	-	-	2480	17.1	860	-	-	-	-	-	✓	-	PC, ABS, PC/ABS, COPE	✓	-	-	
CE 3140-65N	Natural	65A	1.00	-	-	-	-	-	-	11.4	550	-	-	-	-	-	✓	-	PC, ABS, PC/ABS, COPE	✓	-	-	
CE 3140-90N	Natural	90A	1.01	28	-	-	-	-	-	16.1	680	-	85	-	-	-	✓	-	PC, ABS, PC/ABS, COPE	✓	-	-	
CE 3320-70	Natural	72A	1.08	-	-	815	5.62	-	-	1490	10.3	350	-	-	-	-	✓	-	PC, ABS, PC/ABS	✓	-	-	
CE 3320-80	Clear	78A	1.17	31	-	825	5.69	1730	11.9	3300	22.8	650	501	88	-	-	✓	-	PC, ABS, PC/ABS	✓	-	-	
CE 3620	Black/Natural	65A	1.00	18	-	442	3.05	-	4.26	1020	7.03	630	232	41	-	-	✓	HB	ABS, PC, PC/ABS, COPE	✓	-	-	
Versaflex™ PKG Series																							
PKG 4570	Translucent	74A	1.07	12	-	529	-	754	-	1083	-	646	248	-	✓	-	✓	-	-	-	-	-	
PKG 4465	Translucent	63A	0.88	10	-	291	-	425	-	514	-	489	132	-	✓	-	✓	-	PC, ABS	-	-	-	
Versaflex™ Special Series																							
2800-17	Flesh	00 018	0.85	15	-	6	-	11	-	167	-	1259	46	-	-	-	✓	-	None	-	-	-	
2820-55N	Translucent	55A	0.91	11	-	392	-	650	-	1088	-	616	192	-	-	-	✓	-	-	-	-	-	
XP 2850	Natural	53A	0.89	-	-	-	-	-	-	616	-	541	-	-	-	-	-	-	PP, PE	✓	✓	-	



GENERAL PROPERTIES					TENSILE PROPERTIES								REGULATORY					BONDING		PROCESS			
Color	Hardness	Specific Gravity	Compression Set @ 23°C	Compression Set @ 100°C	100% Modulus		300% Modulus		Tensile	Strength	Elongation	Tear Strength		Food Contact	ISO 10993	USP VI	RoHS	UL 94	Suitable Substrates	Injection	Extrusion	Blow	
	ASTM Shore A	ASTM	ASTM %	ASTM %	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM %	ASTM pli	ASTM kN/m										
reSound™ REC Recycled Content Series																							
VX2800-9003 C	Natural	47A	0.94	-	-	127	-	168	-	250	-	585	72	-	-	-	-	-	-	PP	✓	-	-
VX2800-9004 C	Natural	54A	0.95	-	-	176	-	217	-	311	-	581	85	-	-	-	-	-	-	PP	✓	-	-
VX2800-0001 I	Black	65A	0.89	-	-	-	-	-	-	650	4.48	600	-	-	-	-	-	-	-	PP	✓	-	-
VX2800-0001 I	Natural	65A	0.89	-	-	-	-	-	-	784	5.41	690	-	-	-	-	-	-	-	PP	✓	-	-
VX2800-0001 C	Black	65A	0.89	-	-	-	-	-	-	900	6.21	670	-	-	-	-	-	-	-	PP	✓	-	-
VX2800-0002 I	Black	65A	0.88	-	-	-	-	-	-	1020	7.05	670	-	-	-	-	-	-	-	PP	✓	-	-
VX2800-0003 C	Gray	60A	0.88	26	-	-	-	-	-	831	-	620	-	-	✓	-	-	-	-	PP	✓	-	-
VX0100-0001 AR I	Black	78A	1.05	-	-	-	-	-	-	1400	9.65	700	-	-	-	-	✓	-	-	PC, ABS, PC/ABS	✓	-	-
reSound™ BIO Bio-based Series																							
RS7900-0001 30N	Natural	31A	1.00	-	-	-	-	203	1.4	564	3.89	700	-	-	-	-	✓	-	-	PP	✓	-	-
RS7900-0001 45N	Natural	48A	1.11	-	-	-	-	288	1.99	759	5.23	690	-	-	-	-	✓	-	-	PP	✓	-	-
RS7900-0001 60N	Natural	59A	1.11	-	-	-	-	361	2.49	920	6.34	730	-	-	-	-	✓	-	-	PP	✓	-	-
RS7900-0001 70N	Natural	69A	1.09	-	-	-	-	501	3.45	1110	7.69	730	-	-	-	-	✓	-	-	PP	✓	-	-
RS2800-0001 30N	Natural	33A	0.85	-	-	-	-	215	1.48	514	3.54	670	-	-	-	-	✓	-	-	PP	✓	-	-
RS2800-0001 45N	Natural	49A	0.85	-	-	-	-	308	2.12	807	5.56	750	-	-	-	-	✓	-	-	PP	✓	-	-
RS2800-0001 60N	Natural	63A	0.87	-	-	-	-	438	3.02	1090	7.51	710	-	-	-	-	✓	-	-	PP	✓	-	-
RS2800-0001 70N	Natural	71A	0.86	-	-	-	-	583	4.02	1120	7.71	640	-	-	-	-	✓	-	-	PP	✓	-	-
RS2800-0002 70N	Natural	75A	0.88	-	-	471	-	-	-	590	-	239	129	-	-	-	✓	-	-	PP, PE	✓	-	-



ONFLEX™

GENERAL PROPERTIES					TENSILE PROPERTIES								REGULATORY					BONDING		PROCESS		
Color	Hardness	Specific Gravity	Compression Set @ 23°C	Compression Set @ 100°C	100% Modulus		300% Modulus		Tensile	Strength	Elongation	Tear Strength		Food Contact	ISO 10993	USP VI	RoHS	UL 94	Suitable Substrates	Injection	Extrusion	Blow
	ASTM Shore A	ASTM	ASTM %	ASTM %	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM %	ASTM pli	ASTM kN/m									
OnFlex™ General Purpose Series																						
G7705 B	Black	42	1.20	-	-	-	-	287	1.98	491	3.39	675	-	-	-	-	✓	-	PP	✓	✓	-
G7705 N	Natural	44	1.18	-	-	-	-	316	2.18	463	3.19	608	-	-	-	-	✓	-	PP	✓	✓	-
G7720 B	Black	57	1.16	-	-	-	-	388	2.68	716	4.94	710	-	-	-	-	✓	HB	PP	✓	✓	-
G7720 N	Natural	55	1.17	-	-	-	-	391	2.7	782	5.39	760	-	-	-	-	✓	HB	PP	✓	✓	-
G7820 B	Black	92A	1.13	-	-	-	-	940	6.48	1926	13.28	657	-	-	-	-	✓	-	PP	✓	✓	-
G7820 N	Natural	92A	1.14	-	-	-	-	987	6.81	1984	13.68	652	-	-	-	-	✓	-	PP	✓	✓	-
OnFlex™ AF Series																						
AF 7210-50B	Black	50A	1.00	22	-	218	-	435	-	856	-	650	126	-	-	-	✓	-	PP	-	-	-
AF 7210-70B	Black	70A	1.00	31	-	451	-	635	-	1256	-	692	175	-	-	-	✓	-	PP	-	-	-
AF 7210-80B	Black	80A	1.00	32	-	501	-	721	-	1300	-	680	206	-	-	-	✓	-	PP	-	-	-
AF 7215-60B	Black	60A	1.00	26	-	395	-	561	-	1095	-	673	142	-	-	-	✓	-	PP	-	-	-
AF 7215-80B	Black	80A	1.00	29	-	658	-	827	-	1435	-	607	205	-	-	-	✓	-	PP	-	-	-
AF 7215-90B	Black	90A	1.00	33	-	819	-	1036	-	1667	-	568	282	-	-	-	✓	-	PP	-	-	-
OnFlex™ LO Series																						
LO 7120-45N	Natural	45A	1.15	-	-	-	-	325	2.24	386	2.66	700	-	-	-	-	✓	-	PP	✓	-	-

GLS™ TPES WITH ANTIMICROBIAL TECHNOLOGY

OnFlex™ 7120-45B AM	Black	45A	1.13	21	-	-	-	-	-	586	-	-	-	-	-	-	✓	-	PP	✓	-	-
Versaflex™ GP 281-40N AM US	Translucent	45A	0.87	16	-	-	-	-	-	651	-	700	103	-	-	-	✓	-	PP	✓	-	-
Versaflex™ CE 3120-65 AM	Natural	67A	1.15	-	-	-	-	-	-	1100	-	590	-	-	-	-	✓	-	PC, ABS, PC / ABS, COPE	✓	-	-



DYNAFLEX™

GENERAL PROPERTIES					TENSILE PROPERTIES								REGULATORY					BONDING		PROCESS			
Color	Hardness	Specific Gravity	Compression Set @ 23°C	Compression Set @ 100°C	100% Modulus		300% Modulus		Tensile	Strength	Elongation	Tear Strength		Food Contact	ISO 10993	USP VI	RoHS	UL 94	Suitable Substrates	Injection	Extrusion	Blow	
	ASTM Shore A	ASTM	ASTM %	ASTM %	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM %	ASTM pli	ASTM kN/m										
Dynaflex™ Unfilled Series																							
G2701	Clear	66A	0.90	24	-	490	3.38	643	4.43	1100	7.58	680	240	42	✓	-	-	✓	-	PP	✓	✓	-
G2755	Translucent	55A	0.88	17	-	220	1.52	330	2.28	775	5.34	740	140	25	✓	-	-	✓	-	PP	✓	✓	-
G2780	Translucent	84A	0.90	18	-	840	5.79	1140	7.86	1100	7.58	350	250	44	✓	-	-	✓	-	PE	✓	✓	-
G6713	Translucent	14A	0.88	9	-	57	0.39	94	0.64	224	1.54	650	40	7	✓	-	-	✓	-	PP	✓	-	-
Dynaflex™ General Purpose Series																							
G7920	Natural/Black	20A	1.01	17	60	111	-	166	-	307	2.1	680	49	9	✓	-	-	✓	-	PP	✓	-	-
G7930	Natural/Black	30A	1.05	13	-	130	0.89	200	1.38	480	3.3	650	100	18	✓	-	-	✓	HB	PP	✓	-	-
G7940	Natural/Black	40A	1.18	12	-	180	1.24	295	2.03	520	3.59	580	100	18	✓	-	-	✓	HB	PP	✓	-	-
G7950	Natural/Black	50A	1.18	13	-	250	1.72	360	2.48	660	4.55	620	120	21	✓	-	-	✓	HB	PP	✓	-	-
G7960	Natural/Black	60A	1.18	17	-	310	2.14	380	2.62	920	6.34	760	140	25	✓	-	-	✓	HB	PP	✓	-	-
G7970	Natural/Black	70A	1.18	20	-	380	2.62	450	3.1	955	6.58	720	160	28	✓	-	-	✓	HB	PP	✓	-	-
G7980	Natural/Black	80A	1.18	26	-	530	3.65	590	4.07	980	6.76	620	190	33	✓	-	-	✓	HB	PP	✓	-	-
G7990	Natural/Black	93A	1.17	50	-	814	5.62	960	6.62	1550	10.7	610	345	60	✓	-	-	✓		PP	✓	-	-
Dynaflex™ Special Series																							
G7702-9	Black	37A	1.10	11	28	140	0.96	390	2.68	550	3.79	480	120	21	-	-	-	✓	-	PP	✓	✓	-



GENERAL PROPERTIES					TENSILE PROPERTIES								REGULATORY					BONDING		PROCESS		
Color	Hardness	Specific Gravity	Compression Set @ 23°C	Compression Set @ 100°C	100% Modulus		300% Modulus		Tensile	Strength	Elongation	Tear Strength		Food Contact	ISO 10993	USP VI	RoHS	UL 94	Suitable Substrates	Injection	Extrusion	Blow
	ASTM Shore A	ASTM	ASTM %	ASTM %	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM psi	ASTM MPa	ASTM %	ASTM pli	ASTM kN/m									

DYNALLOY™

Dynalloy™ Series																							
GH 7520-75A	Natural	75A	1.08	-	-	-	-	-	-	1320	9.1	560	-	-	-	-	-	✓	-	PP	-	✓	-
DT 7910W	White	46A	0.95	-	-	245	-	391	-	459	-	816	-	-	✓	-	-	-	-	-	-	✓	-

VERSALLOY™

Versalloy™ Healthcare Series																							
HC 9210-45N	Natural	45A	0.89	19	39	160	1.1	320	2.2	484	3.34	480	100	18	✓	-	✓	✓	-	PP	✓	-	-
HC 9210-55N	Natural	53A	0.89	20	44	208	1.44	335	2.31	580	4	610	120	21	✓	-	✓	✓	-	PP	✓	-	-
HC 9210-70N	Natural	70A	0.89	23	53	356	2.45	510	3.52	780	5.38	590	180	32	✓	-	✓	✓	-	PP	✓	-	-
HC 9220-70	Natural	70A	0.95	17	51	453	3.12	-	-	643	4.43	265	208	36	-	✓	✓	✓	-	PP	✓	✓	-
HC 9220-80	Natural	80A	0.94	18	59	553	3.67	777	5.36	945	6.52	415	208	36	-	✓	✓	✓	-	PP	✓	✓	-
HC 9220-90	Natural	90A	0.94	25	55	1180	8.12	1350	9.33	1945	13.45	620	400	70	-	✓	✓	✓	-	PP	✓	✓	-

Versalloy™ Special Series																							
XL 9045-1	Natural	44A	0.88	19	39	170	1.17	320	2.21	484	3.34	480	85	15	✓	-	-	✓	-	PP	✓	-	-
XL 9055	Natural/Black	53A	0.89	20	43	210	1.45	335	2.3	583	4.02	610	120	21	✓	-	-	✓	HB	PP	✓	-	-
XL 9070-1	Natural	70A	0.89	23	53	360	2.48	512	3.53	788	5.43	580	180	32	✓	-	-	✓	HB	PP	✓	-	-

VERSOLLAN™

Versollan™ PC/ABS OM Series																							
OM 1255NX	Natural	59A	1.05	26	-	280	1.93	492	3.39	955	6.58	650	220	39	-	-	-	✓	HB	ABS, PC, COPE	✓	✓	-
RU 2205-1	Natural	65A	1.16	15	-	380	2.62	610	4.21	2000	13.8	710	270	47	-	-	-	✓	HB	ABS, PC, COPE	✓	✓	-

For further information on specific grades, review technical data sheets.





1.844.4AVIENT
www.avient.com



Copyright © 2022, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.